

PHYSICAL PROPERTIES	AVERAGE VALUES	UNITS	STANDARDS
DENSITY	1,24	g/cm ³	
FLOW RATE (210°C /2.16KG)	8	g/10 min	ISO 1133-A
FLOW RATE (190°C /2.16KG)	3	g/10 min	ISO 1133-A
STEREOCHEMICAL PURITY	96	(% L-isomero)	
RESIDUAL MONOMER	0.3% (max)		
MOISTURE (COULOMETRIC KAR L-FISHER)	400 (max)	ppm	
MELTING TEMPERATURE	155°	°C Tm (DSC)	
GLASS TRANSITION TEMPERATURE	55 - 60°	°C Tg (DSC)	

MECHANICAL PROPERTIES	AVERAGE VALUES	UNITS	STANDARDS
TENSILE MODULUS	3500	MPa	ISO 527-1
TENSILE STRENGTH	45	MPa	ISO 527-1
STRAIN AT YIELD	5% (max)		ISO 527-1
CHARPY NOTCHED IMPACT, 23°C	≤5	kJ/m ²	ISO 179-1eA

PRINTING PROPERTIES	AVERAGE VALUES	UNITS	STANDARDS
NOZZLE TEMPERATURE	190 - 230	°C	
HOT BED TEMPERATURE	50 - 70	°C	
COOLING FAN	ON (100)	%	

SPOOL SIZE

300g

1Kg

DIAMETER

1,75mm

1,75mm / 2,85mm

COLOR

Various

Various

PACKAGING

Reusable bag, spool and silica bag

Reusable bag, spool and silica bag

* The indicated parameters are valid for correctly calibrated printers (PID, mechanical and fuser).
 * Supervised and tested manufacturing process (diameter, color and winding) to guarantee the quality of our product.